


TATRAFAN KXT

COEXTRUDED BIAXIALLY ORIENTED PP FILM

Description and Application

- Both-side heat sealable
Wrapping of various food products, confectioneries, meat products, textiles, etc.
- Excellent optical properties (gloss, haze) and slip properties (tailored for high slip performance)
- Improved barrier properties (moisture, odor) and antiblocking properties



TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUES
Nominal thickness tolerance	DIN 53370	µm	21
		%	+5
Unit weight tolerance	Internal method	g/m ²	19,6
		%	+5
Yield		m ² /kg	51,0
Tensile strength MD (min.) TD (min.)		N/mm ²	130
			250
Elongation at break MD (max.) TD (max.)	DIN EN ISO 527-1/3	%	200
			65
Elasticity modulus MD (min.)		N/mm ²	2700
Water vapour permeability (max.)	ASTM F 1249 23 °C, 85% r.h. 38 °C.90% r.h.	g/m ² .24h	1,4
			3,0
Oxygen permeability (max.)	DIN 53380 23%. 0% r.h.	cm ³ /m ² .24h. 0,1MPa	2250
Dynamic coefficient of friction - film/film out /out side	ASTM D 1894	-	0,3
Seal temperature range	Internal method	°C	110 - 140
Seal strength (min.)	120°C, 1,0s, 0,3MPa	N/15mm	2,0
Shrinkage MD (min.) TD (min.)	130°C. 15min.	%	4,2
			4,2
Gloss (20°) (min.)	ASTM D 2457	%	90
Haze (max.)	ASTM D 1003	%	3,0

* After production ** After storage *** Typical values

TATRAFAN KXT

COEXTRUDED BIAXIALY ORIENTED PP FILM

HANDLING AND STORAGE

The product does not present special safety requirements during handling and storage. In order to maintain their properties and to ensure good processability, the film should be stored avoiding high humidity and high temperature conditions. Do not exceed an ambient temperature of 40°C (transport temperature between (-20 + 30)°C and relative humidity of 80%. The product should be protected away from direct sunlight and heat (steam lines or other). Take measures against electrostatic discharges – the film will accumulate electrostatic charge of the web – it could be caused by an electrical spark (ignition source). Keep away from source of ignition. Use with adequate ventilation.

General notes:

Do not handle or store near an open flame, sources of the heat ignition. Store in cool, dry area, away from direct heat or sunlight (Film for food packaging applications keep away from hazardous chemicals). Film properties are guaranteed for 6 months from the date of production.



AVAILABILITY

KXT	Bobbin		
	Length (m)	Core diameter (mm)	Outside diameter (mm)
21	3300	76,8	310

* Standard

ENVIRONMENT

When disposed of under orderly conditions no environmental damage effects occur. During burning under free air conditions only CO₂, CO and water arise. Does not contain additives based on heavy metals (Cd, Pb, Hg, Cr). This product is expected to persist.

OTHER INFORMATION

This information and recommendation is based on Terichem's best knowledge and belief accurate and reliable as of the date indicated.

However, no representation, warranty or guarantee is made with regards to accuracy, reliability or completeness. Conditions of use of the material are under the control of the user; therefore it is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use.



TATRAFAN, s.r.o.

Štúrova 101
059 21 Svit
Slovakia
tel.: +421 52 715 3285
fax: +421 52 715 2303
mail: sales@tatrafan.com